


Core Data Sheet

Part Number: G63-86

Core Dimensions:

Uncoated (tol. +/-0.25)	After coating	
OD (mm) 7.87	(max)	8.52
ID (mm) 3.96	(min)	3.31
HT (mm) 3.18	(max)	3.83



Physical Characteristics:

Winding area (cm ²)	0.09	Strength (N) typ.	44.0
Surface area (cm ²)	2.77	Weight (grams) typ.	0.87
Coating	Epoxy, Light Blue, 0.2 mm approx. per surface. Voltage breakdown 500Vac.		
Packing	Not available.		

Material:

Grade	86		
Initial Permeability (μi)	147	tol +/-	12
Description	High Flux - gas atomized 80 /20 nickel-iron alloy powder		

Electrical Data:

AL norm (nH)	62.00
AL max. (nH)	66.96
AL min. (nH)	57.04
DC bias at 0.8μi (Oe) typ.	24
Power Losses (mW/cm ³) typ. 50kHz, 1000gauss	600
Total Losses (ohms/H/μi) typ. < 20gauss	0.0

Magnetic Dimensions:

C1 (mm-1)	2.9999
Le (mm)	17.2
Ae (mm ²)	5.7
Ve (mm ³)	98.6

Special Comments

- 1.
2. AL band is +/- 12% for DuraFlux
- 3.

Note: the right to change specification data as required without notice is reserved.