


Core Data Sheet

Part Number: G49-95

Core Dimensions:

Uncoated (tol. +/-0.25)	After coating	
OD (mm) 35.81	(max)	36.46
ID (mm) 22.35	(min)	21.70
HT (mm) 10.46	(max)	11.11



Physical Characteristics:

Winding area (cm ²)	3.75	Strength (N) typ.	484.3
Surface area (cm ²)	57.64	Weight (grams) typ.	50.17
Coating	Epoxy, Dark Blue, 0.2 mm approx. per surface. Voltage breakdown 500Vac.		
Packing	Not available.		

Material:

Grade	95		
Initial Permeability (μi)	125	tol +/-	10
Description	MPP - gas atomized 80 /20 nickel-iron alloy powder.		

Electrical Data:

AL norm (nH)	117.00
AL max. (nH)	126.36
AL min. (nH)	107.64
DC bias at 0.8μi (Oe) typ.	25
Power Losses (mW/cm ³) typ. 50kHz, 1000gauss	400
Total Losses (ohms/H/μi) typ. < 20gauss	0.2

Magnetic Dimensions:

C1 (mm-1)	1.3527
Le (mm)	88.1
Ae (mm ²)	65.1
Ve (mm ³)	5732.7

Special Comments

- 1.
- 2.
- 3.

Note: the right to change specification data as required without notice is reserved.