


Core Data Sheet

Part Number: G60-93

Core Dimensions:

Uncoated (tol. +/-0.25)		After coating	
OD (mm)	12.70	(max)	13.35
ID (mm)	7.62	(min)	6.97
HT (mm)	4.75	(max)	5.40



Physical Characteristics:

Winding area (cm ²)	0.40	Strength (N) typ.	87.0
Surface area (cm ²)	7.59	Weight (grams) typ.	2.77
Coating	Epoxy, Dark Blue, 0.2 mm approx. per surface. Voltage breakdown 500Vac.		
Packing	Not available.		

Material:

Grade	93		
Initial Permeability (μi)	60	tol +/-	5
Description	MPP - gas atomized 80 /20 nickel-iron alloy powder.		

Electrical Data:

AL norm (nH)	27.00		
AL max. (nH)	29.16		
AL min. (nH)	24.84		
DC bias at 0.8μi (Oe) typ.	50		
Power Losses (mW/cm ³) typ. 50kHz, 1000gauss	500		
Total Losses (ohms/H/μi) typ. < 20gauss	1.5		

Magnetic Dimensions:

C1 (mm-1)	2.6940
Le (mm)	30.6
Ae (mm ²)	11.3
Ve (mm ³)	346.9

Special Comments

- 1.
- 2.
- 3.

Note: the right to change specification data as required without notice is reserved.