


Core Data Sheet

Part Number: G62 - 98

Core Dimensions:

Uncoated (tol. +/-0.25)	After coating	
OD (mm) 16.64	(max)	17.29
ID (mm) 10.16	(min)	9.51
HT (mm) 6.35	(max)	7.00



Physical Characteristics:

Winding area (cm ²)	0.73	Strength (N) typ.	148.5
Surface area (cm ²)	13.22	Weight (grams) typ.	7.02
Coating	Epoxy, Dark Blue, 0.2 mm approx. per surface. Voltage breakdown 500Vac.		
Packing	Not available.		

Material:

Grade	98		
Initial Permeability (μi)	173	tol +/-	12
Description	MPP - gas atomized 80 /20 nickel-iron alloy powder.		

Electrical Data:

AL norm (nH)	104.00
AL max. (nH)	112.32
AL min. (nH)	95.68
DC bias at 0.8μi (Oe) typ.	18
Power Losses (mW/cm ³) typ. 50kHz, 1000gauss	400
Total Losses (ohms/H/μi) typ. < 20gauss	0.2

Magnetic Dimensions:

C1 (mm-1)	2.0791
Le (mm)	40.4
Ae (mm ²)	19.4
Ve (mm ³)	786.5

Special Comments

- 1.
- 2.
- 3.

Note: the right to change specification data as required without notice is reserved.